MAHAFAST



MAHAFIX

(Manufacturer & Exporter of Dyestuff & Organic Pigments)

SPECIFICATION OF MAHAFAST YELLOW 4017


| PRODUCT DESCRIPTION | | |
|---------------------|-------------------|--|
| C.I. Name | Pigment Yellow 17 | |
| C.I. No. | 21105 | |
| CAS Registry No. | 4531-49-1 | |
| EU No. | 224-867-1 | |
| Chemical Class | Disazo | |


| FASTNESS PROPERTIES | | |
|---------------------|---------------|--|
| Heat °C Mass Tone | 200°C / 5 min | |
| Light | 7/7 | |
| Weather | 5/5 | |
| Migration | 5/5 | |
| Water | 5/5 | |
| Ethanol | 5/5 | |
| Ethyl Acetate | 5/5 | |
| MEK | 5/5 | |
| Acid | 5/5 | |
| Alkali | 5/5 | |

| APPLICATION | |
|----------------------|-------------|
| Solvent Ink | |
| Water Base Flexo Ink | • |
| Paint (Solvent Base) | |
| Paint (Water Base) | |
| Plastics | • |
| Textile | • |
| • | Recommended |
| 0 | Can be used |

| STANDARD PACKAGING | | |
|--------------------|------------|--|
| Paper Bags | 25 Kgs | |
| Big Bags type | On Request | |

| PHYSICAL DATA | | |
|-----------------------------|-----------------------|--|
| Appearance | Fine Yellow Powder | |
| pH of Aqueous | 6 - 8 | |
| Oil Absorption | 80 - 90 | |
| Bulk Density | 25 - 40 | |
| Specific Gravity (at 20°C). | 1.3 g/cm ³ | |





Our product specific end application information are based upon our current knowledge. They are presented without any representation or warranty concerning the suitability, performance or correctness of the product for a particular application or use. Significant variations can occur between test results and results obtained in actual use. We strongly advise that the customer test the product in the specific intended application under conditions expected during use.

Add: C-1/58 GIDC Ph-2, Ahmedabad, India −382445 (Swww.mahavirpigments.com⊠info@mahavirpigments.com D+91-99134-01856